



Fabric Specifications

Jackets • V-Necks



8900 Series		
Dimension	Specification	Test Method
Composition	97% Polyester 3% Carbon	ASTM D-629
Ounces Per Square Yard	3.54	ASTM D-3776-85
Surface Resistivity	10^{6-7} Ohms Square	DIN 54345
Charge Decay	0.5 seconds per 1000 volts	NFPA-99
Weave	6mm rhomb (warp knit)	
Friction Charges	v1150 volts	JIS L1094-B
Tear Strength (Warp)	1600g	JIS L1096 6.15.5D
Tear Strength (Weft)	1200g	JIS L1096 6.15.5D
Tensile Strength (Warp)	100kg	JIS L1096 6.12A
Tensile Strength (Weft)	54.3kg	JIS L1096 6.12A

MAIL: 1744 Thomas Paine Pkwy Dayton, OH 45459 E-MAIL: sales@elimstat.com WEBSITE: elimstat.com

OFFICE: (937) 993-0300 FAX: (937) 993-0307